

TECHNICAL DATA SHEET

15/07/2020

P515

YORI REC

SOLID

COMPOSITION

82%
RPL

POLYESTER
RECYCLED

18%
EA


ELASTANE
High Chlorine
resistance

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
0906673.0 CENTROCOT






Tested for harmful substances.
www.oeko-tex.com/standard100







WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
195 g/m ²	293 g/m lin.	150 cm	44/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH												
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5													
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	40/50+													
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D 4964 - LOAD 20 Lbs</small>	100% WIDTH <small>(min 85% - max 115%)</small>	140% LENGTH <small>(min 119% - max 161%)</small>												
MODULUS @ % ELONGATION (30% - 50% - 70%)	<table border="1" style="width: 100%; border-collapse: collapse; font-size: 8px;"> <thead> <tr> <th style="width: 33%;">30%</th> <th style="width: 33%;">50%</th> <th style="width: 33%;">70%</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">0.2 - 1.0</td> <td style="text-align: center;">1.1 - 2.6</td> <td style="text-align: center;">3.0 - 7.2</td> </tr> </tbody> </table>	30%	50%	70%	0.2 - 1.0	1.1 - 2.6	3.0 - 7.2	<table border="1" style="width: 100%; border-collapse: collapse; font-size: 8px;"> <thead> <tr> <th style="width: 33%;">30%</th> <th style="width: 33%;">50%</th> <th style="width: 33%;">70%</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">0.0 - 0.8</td> <td style="text-align: center;">0.9 - 1.6</td> <td style="text-align: center;">1.7 - 3.1</td> </tr> </tbody> </table>	30%	50%	70%	0.0 - 0.8	0.9 - 1.6	1.7 - 3.1
30%	50%	70%												
0.2 - 1.0	1.1 - 2.6	3.0 - 7.2												
30%	50%	70%												
0.0 - 0.8	0.9 - 1.6	1.7 - 3.1												
	WIDTH Lbs	LENGTH Lbs												
CARE LABELLING CODES	    													

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET

15/07/2020

P515

YORI REC

PFP

COMPOSITION

82%

RPL

POLYESTER
RECYCLED

18%

EA

ELASTANE
High Chlorine
resistance

OEKO-TEX®

CONFIDENCE IN TEXTILES


STANDARD 100

0906673.0 CENTROCOT






Tested for harmful substances.
www.oeko-tex.com/standard100







WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
195 g/m ²	293 g/m lin.	150 cm	44/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5	
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	40/50+	
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D 4964 - LOAD 20 Lbs</small>	95% WIDTH <small>(min 81% - max 109%)</small>	135% LENGTH <small>(min 115% - max 155%)</small>
MODULUS @ % ELONGATION (30% - 50% - 70%)	<small>30% 50% 70%</small>	<small>30% 50% 70%</small>
	0.6 - 1.8 2.2 - 4.2 5.0 - 10.0	0.0 - 0.3 0.6 - 1.5 1.7 - 3.1
	WIDTH Lbs	LENGTH Lbs
CARE LABELLING CODES	    	

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product we reserve the right to modify these when necessary.