

TECHNICAL DATA SHEET

15/06/2020

N820

OCEAN REC

SOLID

COMPOSITION

74%


PA

NYLON RECYCLED




26%

EA


ELASTANE
High Chlorine resistance



OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
0906673.0 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100

WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
200 g/m ²	300 g/m lin.	150 cm	48/cm	28/cm	±3%

<p>DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</p>	<p>max -5% WIDTH</p>	<p>max -5% LENGTH</p>
<p>RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</p>	<p>4 to 4.5</p>	
<p>ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AS/NZS 4399-1996</p>	<p>50+</p>	
<p>STRETCH TO DYNAMOMETER (±15%) ASTM D 4964 - LOAD 20 Lbs</p>	<p>88% WIDTH (min 74% - max 100%)</p>	<p>150% LENGTH (min 123% - max 167%)</p>
<p>MODULUS @ % ELONGATION (30% - 50% - 70%)</p>	<p>30% 50% 70%</p> <p>0.4 - 1.0 1.1 - 2.5 3.5 - 9.5</p>	<p>30% 50% 70%</p> <p>0.4 - 1.0 1.0 - 2.0 2.0 - 3.5</p>
<p>CARE LABELLING CODES</p>		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product we reserve the right to modify these when necessary.

PROVISIONAL TECHNICAL DATA SHEET

20/03/2020

N820

OCEAN REC

PRINTED

COMPOSITION

74%

RPA


NYLON REC

26%


EA

ELASTANE
High Chlorine
resistance


OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
0906673.0 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100



creora
highcolor




work in eco



UPF 50+

WEIGHT (±5%)		WIDTH IN PATTERN(±2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
200 g/m ²	300 g/m lin.	148 cm	48/cm	28/cm	±3%

<p>DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</p>	<p>max -5% WIDTH</p>	<p>max -5% LENGTH</p>
<p>RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT30 MINUTES PHOTOGRAPHIC RATING STD</p>	<p>4 to 4.5</p>	
<p>ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010</p>	<p>50+</p>	
<p>STRETCH TO DYNAMOMETER (±15%) ASTM D 4964 - LOAD 20 Lbs</p>	<p>80% WIDTH (min 68% - max 92%)</p>	<p>150% LENGTH (min 128% - max 173%)</p>
<p>MODULUS @ % ELONGATION (30% - 50% - 70%)</p>	<p>30% 50% 70%</p>	<p>30% 50% 70%</p>
	<p>0.4 - 1.4 1.8- 4.0 6.0- 14</p>	<p>0.4- 1.0 1.0- 2.0 2.0- 3.5</p>
<p>CARE LABELLING CODES</p>		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product we reserve the right to modify these when necessary.