

PROVISIONAL TECHNICAL DATA SHEET

26/05/2020

P365

ATLANTIS REC

SOLID

COMPOSITION



**78%
PL**

POLYESTER
RECYCLED





**22%
EOL**


ELASTOLEFINE
High Chlorine
resistance



OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
0906673.0 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100

WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
190 g/m ²	285 g/m lin.	150 cm	34/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>ATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5	
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AS/NZS 4399-1996</small>	50+	
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D 4964 - LOAD 20 Lbs</small>	145% WIDTH <small>(min 123% - max 167%)</small>	140% LENGTH <small>(min 117% - max 159%)</small>
MODULUS @ % ELONGATION (30% - 50% - 70%)	<small>30% 50% 70%</small>	<small>30% 50% 70%</small>
	0 - 0.2 0.4 - 1.0 1.1 - 2.3	0.3 - 0.8 1.0 - 2.1 2.1 - 3.7
	WIDTH Lbs	LENGTH Lbs
CARE LABELLING CODES		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product we reserve the right to modify these when necessary.