

TECHNICAL DATA SHEET

30/11/2021

N212 SAND REC SOLID

COMPOSITION



RECYCLED
NYLON








ELASTANE
High Chlorine
resistance



UPF 50+

WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
175 g/m ²	263 g/m lin.	150 cm	46/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	115% WIDTH (min 98% - max 132%)		185% LENGTH (min 157% - max 213%)			
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.2 - 0.7	0.7 - 1.5	1.5 - 2.9	0.1 - 0.4	0.4 - 1.1	1.1 - 1.8
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES	    					

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET

30/11/2021

N212 SAND REC PRINTED

COMPOSITION




RECYCLED
NYLON



ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
175 g/m ²	263 g/m lin.	148 cm	46/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	110% WIDTH (min 94% - max 127%)			168% LENGTH (min 143% - max 193%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.2 - 0.7	0.7 - 1.8	1.8 - 3.8	0.0 - 0.4	0.4 - 1.3	1.3 - 2.0
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET

30/11/2021

N212 SAND REC PFP

COMPOSITION








RECYCLED
NYLON



ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
175 g/m ²	263 g/m lin.	150 cm	46/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	105% WIDTH (min 89% - max 121%)		170% LENGTH (min 145% - max 196%)			
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.3 - 0.9	0.9 - 2.0	2.0 - 4.2	0.0 - 0.4	0.5 - 1.2	1.2 - 2.2
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES	    					

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.