

# TECHNICAL DATA SHEET PROVISIONAL

28/07/2020

## P365 ATLANTIS REC SOLID

### COMPOSITION



TEXTURIZED  
RECYCLED  
POLYESTER








ELASTOLEFIN\*  
High Chlorine  
resistance



UPF 50+

WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
190 g/m <sup>2</sup>	285 g/m lin.	150 cm	34/cm	26/cm	±3%

<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
<b>ULTRAVIOLET PROTECTION FACTOR (U.P. F.)</b> AATCC 183-2010	50+					
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs	145% WIDTH (min 123% - max 167%)		140% LENGTH (min 119% - max 161%)			
<b>MODULUS @ % ELONGATION (30% - 50% - 70%)</b>	30%	50%	70%	30%	50%	70%
	0.0 - 0.2	0.4 - 1.0	1.1 - 2.3	0.3 - 0.8	1.0 - 2.1	2.1 - 3.7
	WIDTH Lbs			WIDTH Lbs		
<b>CARE LABELLING CODES</b>	    					

### SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

\* Elastolefin XLANCE®

# TECHNICAL DATA SHEET PROVISIONAL

12/07/2021

## P365 ATLANTIS REC PFP

### COMPOSITION

**78%**  
PL REC






TEXTURIZED  
RECYCLED  
POLYESTER

**22%**  
EOL

ELASTOLEFIN\*  
High Chlorine  
resistance



WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
190 g/m <sup>2</sup>	285 g/m lin.	150 cm	34/cm	26/cm	±3%

<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max <b>-5%</b> WIDTH		max <b>-5%</b> LENGTH			
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
<b>ULTRAVIOLET PROTECTION FACTOR (U.P. F.)</b> AATCC 183-2010	40/50+					
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs	130% WIDTH (min 111% - max 150%)		130% LENGTH (min 111% - max 150%)			
<b>MODULUS @ % ELONGATION (30% - 50% - 70%)</b>	30%	50%	70%	30%	50%	70%
	0.0 - 0.2	0.6 - 1.2	1.5 - 2.8	0.3 - 0.7	1.3 - 2.4	2.4 - 4.4
	WIDTH Lbs			WIDTH Lbs		
<b>CARE LABELLING CODES</b>	    					

### SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

\* Elastolefin XLANCE®