

TECHNICAL DATA SHEET

16/072020

P508 YUKI REC SOLID

COMPOSITION

87%
PL REC


RECYCLED
POLYESTER

13%
EA

ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
170 g/m ²	255 g/m lin.	150 cm	41/cm	24/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	115% WIDTH (min 98% - max 132%)		120% LENGTH (min 102% -max138%)			
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.0 - 0.8	0.8 - 2.0	1.8 - 3.4	0.0 - 0.8	0.8 - 2.0	1.8 - 3.6
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET

16/07/2020

P508
YUKI REC
PFP

COMPOSITION

87%
PL REC

RECYCLED
POLYESTER

13%
EA

ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
170 g/m ²	255 g/m lin.	150 cm	41/cm	24/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	105% WIDTH (min 89% - max 121%)			115% LENGTH (min 98% -max132%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.2 - 1.0	1.2 - 2.8	3.0 - 6.0	0.0 - 0.8	0.8 - 2.2	2.2 - 4.2
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.